

SPORTS COAT

COATING FOR TENNIS AND BASKETBALL COURTS



DESCRIPTION:

SPORTS COAT is a flexible, hard wearing, 100% acrylic Tennis and Basketball Court coating, with good resistance to water in both acid and alkaline conditions.

ADVANTAGES:

- ✓ Resistant to dilute acids and alkalis and mineral oils
- ✓ Resistant to severe atmospheric pollution, e.g. Gas Plants and Sewage Installations
- ✓ Resistance to spread of flame
- ✓ Resistance to fungal growth
- ✓ Excellent wear and tear resistance

AREAS OF APPLICATION:

SPORTS COAT is especially made for Tennis and Basketball Courts.

SPECIFICATIONS:

Colour	White and Other selected shades
Drying Time	
Surface Dry	1 Hour
Hard Dry	3-4 Hours
Coverage	60-70 sq.ft./litre/coat on smooth surface
Flash Point	Above 30°C.
Application	Brush, Roller or Airless Spray.

PREPARATION & METHOD OF APPLICATION:

Clean the surfaces from loose and flaking materials, dirt, grease, wax etc. Apply one coat of ACRYPRIME-20. Let it dry for 3-4 hours. Fill the visible cracks with ACROSEAL. Let it dry for 8-10 hours. Apply first coat of **SPORTS COAT**. Allow to dry for 8-10 hours. Apply second coat and let it dry for 24 hours.

Brush Application:

No thinning is required.

Airless Spray Application:

Thinning ratio up to 400gms of Thinner per 4 litres paint.

Spray tip aperture: 0.33 mm - 0.38 mm (13-15 thou)

Minimum working pressure: 2000 psi.

CLEANING OF TOOLS:

All tools, equipments, hands can be cleaned with solvents like Xylene, Toluene etc.

SAFETY PRECAUTIONS:

Keep away from naked flames/lights. Do not smoke near application area. Protective gear such as gloves and goggles should be worn when handling the product. Treat any splashes to the skin or eyes with fresh water immediately. Should the product be accidentally swallowed, do not encourage vomiting, but call for immediate medical assistance. Ensure that the container is available for medical attendant to examine any relevant instructions and content details

PACKING:

Available in 4 & 20 Litres.

WARRANTY CLAUSE: The product incorporated and sold is without Warranty expressed or implied, including warranty of Merchantability and fitness for use of this material and upon condition that purchaser shall make the own test to determine the suitability and quality of such products for their particular purpose. The user assumes all risks of use and handling, whether or not in accordance with any statement of the supplier. Supplier's liability if any, for any action arising out of the material being supplied shall be limited to only replacement of material.